

HIGH DENSITY POLYETHYLENE

HDPE

GRADE: 293-285 D

Typical applications

HDPE 293-285 D is intended for processing by extrusion method into film of minimum 5 µm thickness used for cold food packaging and other purposes such as bags, various packages.

TECHNICAL CHARACTERISTICS

	Parameter	Standard
1.	Density, g/cm ³	0,943 - 0,949
2.	Melt flow index (MFI), g/10 min	0,4 - 0,7
3.	Melt flow index spread within a batch, %, maximum	±10
4.	Number of inclusions, pieces, maximum	3
5.	Weight content of ash, %, maximum	0.06
6.	Weight content of volatile substances, %, maximum	0,09
7.	Tensile yield strength, MPa, minimum	17
8.	Rupture strength, MPa, minimum	20.6
9.	Elongation at break, %, minimum	700

Supply form: Pallets

Packing: Product is packed in polyethylene bags (one bag net weight 25.00 ±0,25kg) and stacked on flat pallets with shrink film.

Maximum gross weight of a bundle is 2 tons.

Transport: by all modes of transport.

Storage: polyethylene shall be stored in enclosed dry space preventing from direct sunlight on shelves or pallets at least 5 cm from the floor and at least 1m from heaters, at a temperature max 30°C, relative humidity max 80%

Prior to processing bags with polymer shall be kept in production are for at least 12 hrs.

Information contained herein is provided to the best of our knowledge and is considered true on the revision date. This specification does not release a customer from obligation to check the product as to suitability thereof for the intended application. A producer shall not be liable for any loss and damage that might occur due to use of this information.